

PRODUCT DATA SHEET F-LON® 7150 Series

F-LON® 7150 is an advanced **chemical resistant** coating.

F-LON® 7150 is an excellent fluoropolymer coating and conforms to FDA regulations governing coatings for direct food contact application.

F-LON® 7150 Series

Recommended Dry Film Thickness	50-75 microns
Substrates	Most metallic substrates.
Pre-treatment	Degrease followed by sandblasting.
Application method	Hand spray or automatic spray line.
Curing schedule	380°C
Operating Temperature	-195°C-260°C
Colours available	Sparkling Black.
Typical applications	Chemical containers, vessels requiring good nonstick and chemical protection. Packaging heat seal bars.
Other properties	Chemical resistance Abrasion resistance Corrosion resistance Cryogenic stability Hydrophobic FDA Approved

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL

