

PRODUCT DATA SHEET F-LON® 7180 Series

F-LON® 7180 is an advanced **chemical resistant** coating.

F-LON® 7180 is an excellent fluoropolymer coating and conforms to FDA regulations governing coatings for direct food contact application.

F-LON® 7180 Series

Recommended Dry Film Thickness	75-100 microns
Substrates	Most metallic substrates.
Pre-treatment	Degrease followed by sandblasting.
Application method	Hand spray or automatic spray line.
Curing schedule	380°C
Operating Temperature	-195°C-260°C
Colours available	Black
Typical applications	Sweet moulds, sealing discs and pharmaceutical processing equipment.
Other properties	Chemical resistance Abrasion resistance Corrosion resistance Cryogenic stability Hydrophobic Oleophobic FDA compliant

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL

