

PRODUCT DATA SHEET F-LON® 9000 Series

F-LON® 9000 has an good non-stick and superior abrasion resistance at **High Temperatures**. It also exhibits high level of hardness, heat dissipation, and is capable of corrosion & chemical resistance.

F-LON® 9000 is a patented Ceramic Non-stick coating based on Sol-Gel technology.

Sol-Gel materials are formed from small inorganic particles suspended in solution that gel together to form an inorganic matrix.

F-LON® 9000 is a predominantly inorganic coating with a backbone comprising the elements silicon (Si) and oxygen (O).

F-LON® 9000 Series

| | |
|---------------------------------------|---|
| Recommended Dry Film Thickness | 40 ± 5 µm |
| Substrates | Most metallic substrates. |
| Pre-treatment | Degrease followed by sandblasting. |
| Application method | Hand spray or automatic spray line. |
| Curing schedule | 7-10 min @ peak of 280-320°C (or higher)* |
| Operating Temperature | 450°C |
| Colours available | Grey |
| Typical applications | Whitegoods and its accessories, cookware, bakeware, heating elements, electronic equipment for heat dissipation and electrical insulative properties etc. |
| Other properties | Corrosion resistance Chemical resistance Abrasion resistance Non- stick FDA compliant |

*Substrate: Al panel / Coating: Spray, 300°C / 10min / DFT = 40 ± 5 µm.

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL

Issue 1

