

PRODUCT DATA SHEET F-LON® 7190 Series

F-LON® 7190 is an advanced **chemical resistant** coating.

F-LON® 7190 is a high purity fluoropolymer two layer coating.

F-LON® 7190 Series

Recommended Dry Film Thickness	50-75 microns
Substrates	Most metallic substrates.
Pre-treatment	Degrease followed by sandblasting.
Application method	Hand spray or automatic spray line.
Curing schedule	380°C
Operating Temperature	-195°C-260°C
Colours available	Beige
Typical applications	Water and chemical pumps, rotary actuators and food machinery.
Other properties	Chemical resistance Abrasion resistance Corrosion resistance Cryogenic stability Hydrophobic FDA compliant



This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL